


Armourplan SM

Reinforced Single Ply PVC Roofing Membrane

Product Details

Thickness	1.2mm / 1.5mm
Widths	1.06m / 1.50m / 2.12m
Length	20m
Colour	Mid Grey (nearest RAL 7046) Slate Grey (nearest RAL 7015)
Material	PVC-P
Reinforcement	Woven Polyester Scrim
Product Code	420xxxxx – Mid Grey 430xxxxx – Slate Grey



Introduction

Armourplan SM is a polyester scrim reinforced membrane for mechanically fastened roofing systems on both flat and sloping roofs and is suitable for both new build and refurbishment installations. The membrane is mechanically fastened in the overlap using IKOfix Stress Plates and IKOfix Screws into the deck. Overlaps are hot air welded. Armourplan SM can also be used for ballasted systems or alternatively in adhered systems bonded using Armourplan contact adhesive or Sprayfast PCA adhesive. Armourplan SM is also used as the upstand detailing membrane on all Armourplan SM/SG systems.

Features & Benefits

- BBA Certified 05/4287
- Good UV resistance and durability
- Good mechanical properties and product performance
- Efficient and safe installation
- Secure seam welding quality
- Aesthetically pleasing finish
- Complete range of fixings and accessories available

System Components


To complete the installation of Armourplan SM, the system includes a wide range of accessories, including detailing and walkway membrane, cover strips, preformed corners and outlets, standing seam profile, pre-coated metal sheet for forming edge details, IKOfix fastening systems and termination bars, insulation and vapour control layers, adhesives, cleaners, sealants and rooflights.

Certification

- BBA Agrément Certificate No. 05/4287
- Euro Agrément Procedure
- UBAtc ATG (No. 13/0475)
- Czech Republic Protokol C 010_011555
- Slovakia Co-operating Institute Certifikat 2601A/04/0520/1/c/c04
- Manufactured in accordance with BS EN ISO 14001
- Manufactured in accordance with BES 6001




PVC Contact Adhesive Application



1. Before use, thoroughly stir the Armourplan PVC Contact Adhesive. Replace the container lid when work is interrupted.
2. Apply a primer coat of Armourplan PVC Contact Adhesive using a roller or apply Sprayfast PCA adhesive to the prepared substrate surface, priming only the area of substrate where the membrane will be laid the same day. Allow adhesive to dry.
3. If the substrate is PIR insulation then all the board joints are to be taped using self-adhesive foil faced tape prior to the primer coat being applied.
4. Unroll the Armourplan SM over the primed substrate and fold back approximately half its length.
5. Apply a coat of Armourplan PVC Contact Adhesive using a roller or apply Sprayfast PCA adhesive to the underside of the Armourplan SM membrane ensuring the weld area is kept free of adhesive and allow to become tacky.
6. Carefully roll out the Armourplan SM over the previously primed surface and roll with water filled roller or soft broom to ensure intimate contact between the two surfaces.
7. Fold back other half of the roll of Armourplan SM and repeat the procedure.
8. Unroll the next roll of Armourplan SM, ensuring the end laps are staggered and the side overlaps the previously installed sheet by 60mm.
9. Repeat the adhering process.
10. Fully hot air weld the 60mm side lap, allow to cool completely.
11. Mechanically check the integrity of the cooled weld by running a seam probe or 4mm wide screwdriver (with rounded edges) along the seam applying pressure into the seam.

Important: Armourplan PVC Contact Adhesive must only be applied to 100% dry substrates. Failure to do so could result in the membrane de-bonding.

Mechanically Fastened Application



1. Carefully unroll the Armourplan SM out over the previously prepared substrate. If installing on a profiled metal deck ensure that the membrane is perpendicular to the direction of the deck sheet.
2. Install the IKOfix fasteners, using an appropriate installation tool 35mm from the rear edge. Fasteners must be installed at the fixing centers specified by IKO for the specific project.
3. Unroll the next roll of Armourplan SM ensuring the end laps are staggered and the side overlaps the previously installed sheet by 110mm.
4. Hot air weld the side laps with an automatic welder or hot air gun and allow to cool completely.
5. Mechanically check the integrity of the cooled weld by running a seam probe or 4mm wide screwdriver (with rounded edges) along the seam applying pressure into the seam.
6. In corners and other areas where additional fastening is required install IKOfix fasteners through the roof sheet and cover with a 200mm wide strip of Armourplan. Hot air weld both sides and ends.
7. At upstands and at all roof penetrations secure the Armourplan SM membrane with a toothed bar.
8. Cover 10mm gap in the toothed bars with a 50mm x 50mm piece of Armourplan SM and weld to the roof sheet.
9. Waterproof the toothed bar with the upstand flashing hot air welded to the roof sheet.

NB: This is a guide only – please refer to Armourplan Application Manual for Contractor notes

Further Product Information

Full product literature and technical sheets are available as downloads from our website: www.ikopolymeric.com or on request by email: polymeric.marketing@iko.com

Typical Properties

Characteristic properties	Unit	Method	IKO Armourplan SM120	IKO Armourplan SM150
Thickness +10%/- 5%	mm	EN 1849-2	1.20	1.50
Length +1%/- 0.5%	m	EN 1848-2	20.00	20.00
Width +1%/- 0.5%	m	EN 1848-2	1.06/1.5/2.12	1.06/1.5/2.12
Weight +10%/- 5%	g/m ²	EN 1849-2	1600	2000
Tensile strength (MD/TD) +/- 20%	N/50 mm	EN 12311-2	1250	1250
Elongation at break +/- 20%	%	EN 12311-2	25	25
Tear resistance	N	EN 12310-2	> 150	> 150
Peel strength of joints	N/50 mm	EN 12316-2	>200	>200
Shear strength of joints	N	EN 12317-2	>1000	>1000
Hail resistance	m/s	EN 13583	30	30
Nail Tear	N	EN 12310-1	550	550
Impact Resistance	KPa	EN 12691	10	10
Static Load	Kg	EN 12730	20	20
Dimensional stability 6 hrs at 80°C	%	EN 1107-2	≤ 0.5	≤ 0.5
Flexibility at low temperatures	°C	EN 495-5	-30	-30
External exposure to fire		BS EN 476-3	Ext F.AB	Ext F.AB
		EN 13501	T1 – Pass T2 – Pass T3 – Pass T4 – Pass	T1 – Pass T2 – Pass T3 – Pass T4 – Pass
Water tightness		EN 1928 method B	Pass	Pass
Root Resistance			NPD	NPD
Minimum Overlap (Adhered/Ballasted)	mm		60	60
Minimum Overlap (Mechanically Fastened)	mm		110	110
Minimum welding width (Automatic)	mm		>30	>30
Minimum welding width (Hand Welder)	mm		>60	>60
Welding temperature	°C		385 - 450	385 - 450
Recommended welding speed (Automatic Welder)	m/min		1.8	1.8
EC Declaration of conformity with standard			CE Marked	CE Marked

Whilst every care is taken to see that the information given in this literature is correct and up to date it is not intended to form part of any contract or give rise to any collateral liability, which is hereby specifically excluded. Intending purchasers of our materials should therefore verify with the company whether any changes in our specification or application details or otherwise have taken place since this literature was issued.

Company Registered in England No. 2678296 – Registered Office: Appley Lane North, Appley Bridge, Wigan, Lancashire, WN6 9AB



NS5Plus