


Spectraplan Walkway

Walkway Membrane

Product Details

Thickness	4mm
Width	0.76m
Length	15m
Colour	Dark Grey / Yellow
Material	TPE
Reinforcement	N/A
Product Code	40001576



Introduction

Spectraplan Walkway membrane is a 4mm thick dark grey coloured TPE walkway membrane with yellow demarcation strips either side available in 0.76m wide x 15m long rolls and is hot air welded to the roof surface in a layout as specified by the client. The herringbone patterned walkway membrane provides a slip resistant surface and provides additional protection to the waterproof membrane in areas where mechanical damage is more likely to occur. Spectraplan Walkway membrane can be installed over either mechanically fastened or adhered Spectraplan roofing systems.

Features & Benefits

- Herringbone Patterned
- Contrasting colour for demarcation
- Excellent UV resistance and durability
- Excellent mechanical properties and product performance
- Efficient and safe installation
- Secure seam welding quality

Spectraplan Walkway Installation

1. Before installing the walkway membrane on to the completed roof area thoroughly check the installed Spectraplan membrane for any weak welds, mechanical damage and ensure the area is clean dry and free from any debris or contamination.
2. If the walkway is to be heavily trafficked or Rockwool thermal insulation board has been used a 0.9mm galvanized steel spreader sheet should be installed either beneath the waterproofing membrane or beneath the walkway membrane. The spreader sheet should be wrapped in IKOtex fleece and each corner fixed to the substrate using suitable IKOfix fasteners.
3. Unroll the Walkway Membrane, cut to length if necessary and neatly round off any corners.
4. Hot air weld the Spectraplan Walkway membrane to the Spectraplan membrane beneath carrying out any seam preparation in accordance with the IKO Polymeric Spectraplan installation handbook.
5. Once the welds have cooled check the weld integrity by using a seam probe or 4mm wide screwdriver (with rounded edges) along the seam applying pressure into the seam. Repair any defects as necessary.
6. Repeat the process leaving a 25mm gap between each roll end. Do not overlap the Spectraplan Walkway membrane as the grid pattern may prevent a fully sealed weld being achieved.

Typical Properties

Characteristic properties	Unit	Method	IKO Spectraplan Walkway
Thickness +10%/- 5%	mm	EN 1849-2	4.0
Length +1%/- 0.5%	m	EN 1848-2	15.00
Width +1%/- 0.5%	m	EN 1848-2	0.76
Minimum Overlap	mm		N/A
Minimum welding width (Automatic)	mm		>30
Minimum welding width (Hand Welder)	mm		>60
Welding temperature	°C		550
Recommended welding speed (Automatic Welder)	m/min		1.5

Further Product Information

Full product literature and technical sheets are available as downloads from our website: www.ikopolymeric.com or on request by email: polymeric.marketing@iko.com

Whilst every care is taken to see that the information given in this literature is correct and up to date it is not intended to form part of any contract or give rise to any collateral liability, which is hereby specifically excluded. Intending purchasers of our materials should therefore verify with the company whether any changes in our specification or application details or otherwise have taken place since this literature was issued.

Company Registered in England No. 2678296 – Registered Office: Appley Lane North, Appley Bridge, Wigan, Lancashire, WN6 9AB



n55Plus

IKO Polymeric
Coney Green Road, Clay Cross
Chesterfield, S45 9HZ

Tel: 01257 488 000
Sales: polymeric.sales.uk@iko.com
Technical: polymeric.technical.uk@iko.com